

## Diphyl<sup>®</sup> THT

### Properties

Diphyl<sup>®</sup> THT is a high-performance heat resistant synthetic heat transfer fluid for use in the liquid phase in closed heat transfer systems. It has an extremely high thermal stability with a long operating life.

### Specification

PARAMETER	UNIT	SPECIFICATION	METHOD
Appearance		Colorless pale yellow liquid	
Assay terphenyls, partially hydrogenated	weight-%	min. 99.5	GC
Water content	mg/kg	max. 100	Karl Fischer

*Specification values are subject to constant monitoring.*

### Physical / Chemical Data

PARAMETER	UNIT	VALUE	METHOD
Range of application	°C	0 to 345	
Kinematic viscosity (20°C)	mm <sup>2</sup> /s	102	
Density (20°C)	kg/m <sup>3</sup>	1004	DIN 51562-1
Pour point	°C	-33	DIN ISO 3016
Neutralisation number	mg KOH/g	0.01	DIN 51558 part 1
Maximum film temperature	°C	370	DIN ISO 3016
Initial boiling point (at 1.013 bar)	°C	352	DIN 51558 part 1
Flash point	°C	190	ISO 2719
Autoignition temperature	°C	380	DIN 51794
Solubility in water (at 20°C)	mg/l	0.0001	Quentin method
Surface tension (at 20°C)	mN/m	37.9	OECD ring method
Thermal conductivity	W/m·K	0.109	
Mean specific heat (20°C)	kJ/kg·K	1.54	
Coefficient of thermal expansion	1/K	$8.4 \cdot 10^{-4}$	

*Characteristic data provide further information about the product and are not subject to constant monitoring. They are therefore not binding.*

### Storage / Handling / Labeling

Please refer to our Safety Data Sheet.

### Shelf Life

Tank container: 2 years if stored properly

200 kg drum: 2 years if stored properly and kept in the original sealed packaging.

### Diphyl<sup>®</sup> THT

#### Packaging

Tank container  
200 kg Drum

#### Additional Information

CAS No.:	61788-32-7
EINECS:	262-967-7
REACH:	05-2114710765-48-0000

#### Application

The product is used e.g. for:

- chemical processing plants
- petrochemical processing plants
- waste heat recovery
- PET/PA fiber spinning

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery. In the United States of America the LANXESS business is conducted by LANXESS Corporation, Pittsburgh, PA. Customers in the US are kindly asked to address their requests directly to this legal entity.

Issue number: UVP 57735472; Version 2 / Date of issue: April 10, 2018 / Previous issue from Version 1, April 2017 / Information current as of date of issue. Please contact your LANXESS representative to determine if this publication has been revised.